

New Challenge Best Quality



## Ferro-titanium

< Product standards >

Grade	Product	Chemical composition (% max.)							
		Ti	C	Si	Mn	P	S	Al	Cu
1	OFT-70	70.0	0.1	0.1	0.2	0.01	0.01	0.2	0.1
2	OFT-40	40.0	0.1	0.15	0.3	0.01	0.01	0.2	0.1

## Contact Us

Sales and Marketing Department  
Titanium Sales and Marketing Group

TEL.81-3-5776-3102

FAX.81-3-5776-3111

E-mail:titanium@osaka-ti.co.jp